	me		
Qu	Date		
(H	ETERMINING THE ASPHALT BINDER CONTENT OF HOT MIX A MA) BY THE IGNITION METHOD OP FOR AASHTO T 308	SPHAL	.т
Te	sts Performed According to Procedure?	Yes	No
1.	Oven at correct temperature 538°C (1000°F) or correction Factor temperature?		
2.	Sample reduced to correct size?		
3.	Mass of sample basket assembly recorded to 0.1 g?		
4.	With pan below basket(s) sample evenly distributed in basket(s)?		
5.	Sample conforms to the required mass and mass recorded to 0.1 g?		
6.	Initial mass entered into furnace controller?		
7.	Sample correctly placed into furnace?		
8.	Test continued until stable indicator signals?		
9.	Uncorrected binder content obtained on printed ticket?		
10.	Sample mass determined to nearest 0.1 g.?		
If'	'No" was discrepancy corrected? Date of "Split Sample"	Yes	No
			<u> </u>
	Signature of Examiner		

Part 8 - Materials Manual	July 2005
Indonesident Assumes	

Qua	alification # Date		
PA	EORETICAL MAXIMUM SPECIFIC GRAVITY AND DENSITY (VING MIXTURES P FOR AASHTO T 209	OF BITUM	IINOU
Tes	ts Performed According to Procedure?	Yes	No
1.	Sample reduced to correct size?		
2.	Particles carefully separated insuring that aggregate is not fractured?		
3.	After separation, fine aggregate particles not larger than 6.4 mm (1/4in)?		
4.	Sample at room temperature?		
5.	Mass of bowl or flask & cover determined to 0.1 g?		
6.	Mass of sample and bowl or flask & cover determined to 0.1 g?		
7.	Mass of sample calculated and conforms to required size?		
8.	Water at approximately 25°C (77°F) added to cover sample?		
9.	Entrapped air removed using partial vacuum for 15 ±2 min?		
	Container and contents agitated continuously by mechanical device or manually by vigorous shaking at intervals of about 2 minutes?		
11.	Flask filled with water?		
12.	Flask then placed in constant temperature water bath (optional)?		
13.	Contents at 25 ± 1 °C (77 ± 1.8 °F) or temperature taken and Table 2 in FOP used?		
	Mass of filled flask determined to 0.1 g, 10 ± 1 minutes after removal of entrapped air completed?		
15.	Flask mass with water determined to nearest 0.1 g?		
16.	Specific gravity calculated correctly and to 0.001?		
17.	Density calculated correctly and to 1 kg/m ³ (0.1 lb/ft ³)?		
If "	No" was discrepancy corrected? Date of "Split Sample"	Yes	No

Part 8 - Materials Manual	July 2005
Indonesident Assumes	

	ıme			
Qι	ıalif	ication # Date		
SA	\T L	SPECIFIC GRAVITY OF COMPACTED BITUMINOUS MIXTU RATED SURFACE-DRY SPECIMENS FOR AASHTO T 166	JRES U	SING
Te	sts l	Performed According to Procedure?	Yes	No
1.	Ma	ass of dry sample in air determined.		
	a.	Dried overnight at 52 ± 3 °C (125 ± 5 °F) and at successive 2-hour intervals to constant mass?		
	b.	Cooled to room temperature, $25 \pm 5^{\circ}$ C (77 $\pm 9^{\circ}$ F)?		
	c.	Dry mass determined to 0.1g?		
2.	Im	mersed weight determined.		
	a.	Water at $25 \pm 1^{\circ}$ C (77 $\pm 1.8^{\circ}$ F)?		
	b.	Immersed at 4 ± 1 minutes?		
	c.	Immersed weight determined to 0.1g		
3.	Sa	mple rapidly surface dried with damp cloth?		
4.	Sa	turated surface-dry (SSD) mass determined to 0.1g?		
5.	Sp	ecific Gravity calculated to 0.001?		
N(Step 1 is not required for laboratory prepared specimens, for specimens ob cores, step 1 may be performed last.	tained in	the field,
If '	"No	"was discrepancy corrected? Date of "Split Sample"	Yes	No
		Signature of Examiner		

Part 8 - Materials Manual	July 2005

	me alification # Date		
	ECHANICAL ANALYSIS OF EXTRACTED AGGREGATE OP FOR AASHTO T 30		
Te	sts Performed According to Procedure?	Yes	No
1.	Total dry mass determined to 0.1 g		
2.	Dry mass agrees with sample mass after ignition ($M_{\rm f}$) from AASHTO T 308 within 0.1% of $M_{\rm f}$?		
3.	Sample placed in container and covered with water?		
4.	Wetting agent added?		
5.	Contents of container agitated vigorously?		
6.	Wash water poured through proper nest of two sieves?		
7.	Washing continued until wash water is clear and no wetting agent remaining?		
8.	Washed material coarser than 75 μ m (No. 200) dried to constant mass at 110 ±5°C (230 ±9°F)?		
9.	Dry mass after washing determined to 0.1 g?		
10.	Material sieved on specified sieves?		
11.	Mass of each fraction of aggregate, including minus 75 μm (No. 200), determined and recorded to 0.1 g?		
12.	Percent passing on each sieve determined correctly to the nearest 0.1% and nearest 0.1% on the 75 μm (No. 200)?		
13.	Percent passing on each sieve reported correctly to the nearest 1% and nearest 0.1% on the 75 μm (No. 200)?		
14.	Does summation of sieve masses check total washed dry mass to within 0.2 percent?		
If '	'No" was discrepancy corrected? Date of "Split Sample"	Yes	No
			<u>—</u>
	Signature of Examiner		

Independent Assurance	Part 8 - Materials Manual	July 2005
T 1 1 4 A		

Na Qu	me Date	;	
	RATORY COMPACTION OF HMA MIXTURES OP FOR AASHTO T 312		
Te	sts Performed According to Procedure?	Yes	No
1.	Aged mix brought to compaction temperature?		
2.	Base and upper plate of the mold heated to compaction temperature?		
3.	Paper disks placed on top and bottom?		
4.	Mix poured into mold all at once?		
5.	Pressure applied at 600 kPa ±18 kPa?		
6.	Specified number of gyrations applied?		
7.	Compacted specimen removed from mold and allowed to cool to room temperature?		
8.	Sample correct height at required gyrations (115 ±5mm)?		
9.	Corrected relative density calculated correctly?		
If '	'No" was discrepancy corrected? Date of "Split Sample"	Yes	No
			<u> </u>
	Signature of Evaminer		<u>—</u>

Part 8 - Materials Manual	July 2005